






DESCRIPTION			
Total thickness	EN 428	mm	2.00
	ASTM F386-02	inch	0,08
Wearlayer thickness	EN 429	mm	> 1
	ASTM F410-02	inch	≥ 0.039
Weight	EN 430	g/sq.m	2580 - 2680
		lbs/sq.ft	0.53 - 0.57
Width of sheet	EN 426	cm	200
	-	feet - inch	6'6"
Length of sheet	EN 426	lm	20
	-	feet - inch	66'
CLASSIFICATION			
Norm / Product specification	-	-	EN 649
	ASTM F1303-04	-	in progress
European classification	EN 685	class	34 - 43
Fire rating	EN 13 501-1	class	Bfl-s1
Static electrical propensity	EN 1815	kV	< 2
Slip resistance (1)	DIN 51 130	class	R10
PERFORMANCES			
Wear resistance	EN 660.2	mm ³	≤ 2.0
Wear group	EN 649 - EN 651	-	T
Type binder content	ISO 10582	type	I
Dimensional stability	EN 434	%	≤ 0.40
Residual indentation (requirement)	EN 433	mm	≤ 0.10
Residual indentation (measure)		mm	≈ 0.02
Impact sound insulation	EN ISO 717-2	dB	8
Castor chair test (type W)	EN 425	-	OK
Thermal conductivity	EN 12 524	W/(m.K)	0.25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Surface treatment	-	-	ProtecSol® 2
Chemical products resistance (2)	EN 423	-	OK
Treatment	-	-	Sanosol®
Anti-bacterial activity (E. coli - S. aureus - MRSA) (3)	ISO 22196	-	> 99.9% inhibits growth
ENVIRONMENT / INDOOR AIR QUALITY			
TVOC after 28 days	ISO 16000-6	µg/m ³	< 10
Certification			Floorscore™
CE MARKING			
	EN 14041	  	
			

(1) For lifetime sustainable wet resistance, please refer to Tarasafe ranges.

(2) Regarding the resistance to chemicals, please download the corresponding leaflet from our website.

(3) The implementation of an effective cleaning regime is the most important defence against infection.