

### DESCRIPTION

Total Thickness	EN ISO 24346	mm	5		
Thickness of the wearlayer	EN ISO 24340	mm	0,70		
Weight	EN ISO 23997	g/sqm	7670		
Size	EN ISO 24342	mm	212x1238,8	239,6x1460,8	388,8x728,7
Number of planks /tiles and sqm per box	-	-	7 / 1,84 sqm	6 / 2,10 sqm	6 / 1,70 sqm

### CLASSIFICATION

Norm/Product Specification	-	-	EN ISO 10582		
European Classification	EN ISO 10874	class	34 – 43		
Fire Rating	EN 13 501-1	class	Bfl-s1		
Static Electrical Propensity	EN 1815	kV	< 2		
Slip Resistance Wet	DIN 51 130	class	R10		


### PERFORMANCES

Wear Resistance	EN 660.2	mm3	≤ 2.0		
Wear Group		group	T		
Type Binder content	ISO 10582	group	I		
Room Impact	NF S 31074	dB	79		
Impact sound insulation	EN ISO 717-2	dB	4		
Dimensional stability (norm)	EN ISO 23999	%	≤ 0.15		
Dimensional stability (average measured value)	-	%	≈ 0.05		
Residual Indentation	EN ISO 24343-1	mm	≤ 0.10		
Castor chair test	ISO 4918	-	OK		
Thermal Conductivity	EN ISO 10456	W/(m.K)	0.25		
Colour Fastness	EN 105 - B02	degree	≥ 6		
Surface Treatment	-	-	Protecshield®		
Chemical Products Resistance	EN ISO 26987		OK		

### ENVIRONMENT / INDOOR AIR QUALITY

TVOC after 28 days	ISO 16000-6	µg/ m3	< 10		
--------------------	-------------	--------	------	--	--

### CE MARKING

	EN 14041		